

3000 NET

SUNSHADOW SOLAR SCREEN



TEXTSTYLE




96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Page 1

Received:08/15/2016	Completed:08/16/2016	Letter: R	BG	P.O.#:	Test Report #:	3-14811-0-
Client's Identification	Style: 3000 NET. Composition: 75% PVC, 25% Polyester. Weight: 13.12 oz/y ² . Thickness: 0.022". Product End Use: Interior Roller Shades.					
Tested For: Jessica Bondell	Key Test: CA 1237 Sm				195	
Rollese Acmeda, Inc. 200 Harvard Avenue Stamford, CT 06902			Tel: 1-(203)-964-1573		Ext:	
			Fax: 1-() - -			
LE: 1993; V 09/15 NTR 04/16 PC: 1H /jd SM/mg						
TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - INTERIOR MATERIALS QUALIFICATION						
RESULTS REPORTED: <input checked="" type="checkbox"/> Initially <input type="checkbox"/> After 3 dry cleanings <input type="checkbox"/> After 5 launderings @ 160°F						
RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)		
Warp:	1	0.0	0	5.4		
	2	3.2	0	5.5		
	3	0.0	0	5.0		
	4	7.6	0	5.0		
	5	4.3	0	5.1		
	Avg:	3.0				
Fill:	6	6.6	0	4.6		
	7	0.0	0	5.0		
	8	3.2	0	5.5		
	9	5.2	0	5.0		
	10	3.3	0	5.0		
	Avg:	3.7				
APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 12.8 oz/yd ²						
ACCEPTANCE CRITERIA:						
Afterflame:	4.0 seconds maximum average for warp or fill					
Afterglow:	(see Note #2 below)					
Char Length:	6.0 inches maximum for any individual specimen					
NOTES:						
1. An asterisk (*) next to any char length measurement indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd ² .						
2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria.						
(Page 1 of 2)						

3000 NET

SUNSHADOW SOLAR SCREEN




TEXTSTYLE



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Page 2

Received:08/15/2016	Completed:08/16/2016	Letter: R	BG	P.O.#:	Test Report #:	3-14811-0-
Client's Identification	Style: 3000 NET. Composition: 75% PVC, 25% Polyester. Weight: 13.12 oz/y ² . Thickness: 0.022". Product End Use: Interior Roller Shades.					
Tested For: Jessica Bondell	Key Test: CA 1237 Sm					195
Rollease Acmeda, Inc. 200 Harvard Avenue Stamford, CT 06902	Tel: 1-(203)-964-1573		Ext:			
	Fax: 1-()- -					
<p>CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:</p> <p>[x] Complies; [] Does not comply</p> <p>REMARKS: None.</p> <p>NOTE: The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:</p> <ol style="list-style-type: none"> 1. A maximum afterflame of 4 seconds is permitted as opposed to 1 second. 2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement. 3. Ten specimens are tested in lieu of 6 specimens. <p>This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.</p> <p>CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.</p> <p>  ----- AUTHORIZED SIGNATURE GOVMARK /ec /mo </p> <p style="text-align: right;">AUG 18 2016</p> <p style="text-align: center;"><i>Ms. Phyllis Pettit</i></p>						
(Page 2 of 2)						

The results contained in this report relate only to item(s) tested. The test report shall not be reproduced, except in full, without written approval from Govmark.