

4000 NET

SUNSHADOW SOLAR SCREEN



TEXTSTYLE



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com


Page 1

Received:08/04/2016	Completed:08/05/2016	Letter: B	BG	P.O.#:	Test Report #:	3-14675-0-																																																									
Client's Identification	Style: 4000 NET. Composition: 27% Polyester, 73% PVC. Weight: 15.34 oz/y ² . Thickness: 0.027". End Use: Interior Roller Shades.																																																														
Tested For: Jessica Bondell	Rollese Acmeda, Inc. 200 Harvard Avenue Stamford, CT 06902			Key Test: CA 1237 Sm		195																																																									
				Tel: 1-(203)-964-1573	Ext:																																																										
				Fax: 1-()- -																																																											
<p>LE: 1993; V 09/15 NTR 04/16 PC: 1H /jd SM/mg</p> <p>TEST PERFORMED: California Fire Marshal Title 19: Section 1237 (Proposed Revision 8/9/93) Fire Resistance; Small Scale Test - INTERIOR MATERIALS QUALIFICATION</p> <p>RESULTS REPORTED: <input checked="" type="checkbox"/> Initially <input type="checkbox"/> After 3 dry cleanings <input type="checkbox"/> After 5 launderings @ 160°F</p> <table border="1"> <thead> <tr> <th>RESULTS:</th> <th>Specimen #</th> <th>Afterflame (seconds)</th> <th>Afterglow (seconds)</th> <th>Char Length (inches)</th> </tr> </thead> <tbody> <tr> <td rowspan="5">Warp:</td> <td>1</td> <td>3.4</td> <td>0</td> <td>4.1</td> </tr> <tr> <td>2</td> <td>2.2</td> <td>0</td> <td>4.2</td> </tr> <tr> <td>3</td> <td>0.0</td> <td>0</td> <td>3.9</td> </tr> <tr> <td>4</td> <td>2.4</td> <td>0</td> <td>3.5</td> </tr> <tr> <td>5</td> <td>1.7</td> <td>0</td> <td>3.9</td> </tr> <tr> <td></td> <td>Avg:</td> <td>1.9</td> <td></td> <td></td> </tr> <tr> <td rowspan="5">Fill:</td> <td>6</td> <td>2.4</td> <td>0</td> <td>3.5</td> </tr> <tr> <td>7</td> <td>4.0</td> <td>0</td> <td>4.2</td> </tr> <tr> <td>8</td> <td>1.9</td> <td>0</td> <td>3.8</td> </tr> <tr> <td>9</td> <td>6.3</td> <td>0</td> <td>4.0</td> </tr> <tr> <td>10</td> <td>0.0</td> <td>0</td> <td>4.0</td> </tr> <tr> <td></td> <td>Avg:</td> <td>2.9</td> <td></td> <td></td> </tr> </tbody> </table> <p>APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 16.4 oz/yd²</p> <p>ACCEPTANCE CRITERIA:</p> <p>Afterflame: 4.0 seconds maximum average for warp or fill Afterglow: (see Note #2 below) Char Length: 6.0 inches maximum for any individual specimen</p> <p>NOTES:</p> <ol style="list-style-type: none"> 1. An asterisk (*) next to any char length measurement indicates that a part of the char length is melt away due to heat from the flame source and not from propagating flame. Therefore, the sample submitted meets the requirements of Title 19 - California Code of Regulations, Section 1237 and 1237.1 for materials weighing less than 4 oz/yd². 2. Afterglow is required to be reported; however, it is not factored into the Acceptance Criteria. <p>(Page 1 of 2)</p>							RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)	Warp:	1	3.4	0	4.1	2	2.2	0	4.2	3	0.0	0	3.9	4	2.4	0	3.5	5	1.7	0	3.9		Avg:	1.9			Fill:	6	2.4	0	3.5	7	4.0	0	4.2	8	1.9	0	3.8	9	6.3	0	4.0	10	0.0	0	4.0		Avg:	2.9		
RESULTS:	Specimen #	Afterflame (seconds)	Afterglow (seconds)	Char Length (inches)																																																											
Warp:	1	3.4	0	4.1																																																											
	2	2.2	0	4.2																																																											
	3	0.0	0	3.9																																																											
	4	2.4	0	3.5																																																											
	5	1.7	0	3.9																																																											
	Avg:	1.9																																																													
Fill:	6	2.4	0	3.5																																																											
	7	4.0	0	4.2																																																											
	8	1.9	0	3.8																																																											
	9	6.3	0	4.0																																																											
	10	0.0	0	4.0																																																											
	Avg:	2.9																																																													

File Copy

4000 NET

SUNSHADOW SOLAR SCREEN



TEXTSTYLE



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Page 2

Received:08/04/2016	Completed:08/05/2016	Letter: B	BG	P.O.#:	Test Report #:	3-14675-0-
Client's Identification	Style: 4000 NET. Composition: 27% Polyester, 73% PVC. Weight: 15.34 oz/y ² . Thickness: 0.027". End Use: Interior Roller Shades.					
Tested For: Jessica Bondell	Key Test: CA 1237 Sm				195	
Rollease Acmeda, Inc. 200 Harvard Avenue Stamford, CT 06902	Tel: 1-(203)-964-1573		Ext:			
	Fax: 1-()- -					

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply

REMARKS: None.

NOTE: The number of test specimens and Acceptance Criteria are based on a proposed revision issued and implemented by the California State Fire Marshal in August 1993. In substance, the following has occurred:

1. A maximum afterflame of 4 seconds is permitted as opposed to 1 second.
2. It was clarified that the char length maximum of 6 inches applies to any individual specimen and is not an average requirement.
3. Ten specimens are tested in lieu of 6 specimens.

This report issues the conclusion to Section 1237 based on the California State Fire Marshal's continued endorsement of the proposed revision.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

AUTHORIZED SIGNATURE
 GOVMARK
 /pm/mo

Robert I. Brown

AUG 08 2016

(Page 2 of 2)

The results contained in this report relate only to item(s) tested. The test report shall not be

File Copy